

TPU CHEMICAL RESISTANCE CHART

Ratings Guide

G – Should have little or no effect on the material at the given concentration and temperature

Moderate – Some effect on the material at the given concentration and temperature. Caution advised.

X – Not recommended.

CHEMICALS	CONC.	RATING All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Acetaldehyde		X (X)
Acetamide		X (X)
Acetic acid	3%	G (G)
Acetic acid	10%	M (M)
Acetic acid	25%	X (M)
Acetic acid	100%	X (X)
Acetic anhydride	50%	X (X)
Acetone		X (X)
Acetylene		X (X)
Acrylonitrile		X (X)
Adipic acid		M (M)
Allyl alcohol		X (X)
Allyl chloride		X (X)
Alum (Potassium Aluminum Sulfate)		G (G)
Aluminum acetate		X (G)
Aluminum chloride		M (M)
Aluminum hydroxide		M (G)
Aluminum nitrate		M (G)
Aluminum phosphate		G (G)
Aluminum potassium sulfate		M (M)
Aluminum sulfate		M (G)
Ammonia, liquid	100%	X (X)
Ammonia, aqueous	25%	X (X)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Ammonium acetate		X (X)
Ammonium carbonate		X (X)
Ammonium chloride	3%	M (G)
Ammonium fluoride		X (X)
Ammonium hydroxide		X (X)
Ammonium nitrate		G (G)
Ammonium persulfate		M (G)
Ammonium phosphate		M (G)
Ammonium sulfate		G (G)
Ammonium thiocyanate		M (G)
Amyl acetate, normal		X (X)
Amyl alcohol		M (X)
Amyl chloride		X (X)
Aqua Regia		X (X)
Aniline		X (X)
Aniline hydrochloride		X (X)
Animal Fats		G (G)
Antimony chloride	50%	M (G)
Antimony chloride	100%	X (X)
Arsenic acid		X (X)
ASTM Fuel A		G (G)
ASTM Fuel B		X (M)
ASTM Fuel C		X (M)
Barium chloride		G (G)
Barium hydroxide		M (G)
Barium sulfate		G (G)
Barium sulfide		G (G)
Beer		G (G)
Benzaldehyde		X (X)
Benzene		X (X)
Benzoic acid		X (X)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Benzyl benzoate		X (X)
Benzyl alcohol		X (X)
Benzyl chloride		X (X)
Biphenyl, polychlorinated		G (G)
Boric acid		M (G)
Brake fluid		X (X)
Brine		M (M)
Bromine		X (X)
Bromine water		X (X)
Bromobenzene		X (X)
Butadiene		G (G)
Butane		M (M)
Butyl acetate, normal		X (X)
Butyl benzoate		G (G)
Butyl alcohol, normal		X (X)
Butyl carbitol		X (X)
Butyl stearate		M (M)
Butylene glycol		M (M)
Butylphenol		X (X)
Butyric acid		X (X)
Calcium acetate		G (G)
Calcium bicarbonate		G (G)
Calcium bisulfate		M (M)
Calcium bisulfite		M (M)
Calcium carbonate		G (G)
Calcium chloride		M (G)
Calcium hydroxyde		M (G)
Calcium hypochlorite		X (X)
Calcium nitrate		G (G)
Calcium oxide		G (G)
Calcium phosphate		G (G)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Calcium sulfate		M (G)
Calcium sulfide		G (G)
Camphor		X (X)
Carbitol		X (X)
Carbolineum		X (X)
Carbon bisulfide		M (G)
Carbon dioxide, damp		G (G)
Carbon dioxide, dry		G (G)
Carbon tetrachloride		X (X)
Carbonic acid		G (G)
Castor oil		G (G)
Chloral hydrate		X (X)
Chloramine		G (G)
Chlorine, Wet		X (X)
Chlorine, Dry		X (X)
Chlorine water	3%	X (M)
Chlorobromomethane		X (M)
Chloroacetic acid		X (X)
Chlorobenzene		X (X)
Chlorobiphenyl		X (X)
Chloroform		X (X)
Chlorosulfonic acid		X (X)
Chromic acid	10%	X (X)
Chromic acid	25%	X (X)
Chromic acid	50%	X (X)
Citric acid		M (G)
Coal Tar		M (M)
Coconut fatty alcohol		G (G)
Coconut oil		G (G)
Cod-liver oil		G (G)
Copper acetate		X (X)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Copper chloride		M (G)
Coper cyanide		M (G)
Copper fluoride		X (X)
Copper nitrate		X (M)
Copper sulfate		M (M)
Cotton oil		G (G)
Creosote		X (G)
Cresol (-mixtures)		X (X)
Crotonaldehyde		M (M)
Crude oil		G (G)
Cumene		X(X)
Cupric hydroxide		G (G)
Cyclohexalimine		X (X)
Cyclohexanol		G (G)
Cyclohexanone		X (X)
Decahydronaphthalene		M (X)
Densodrin W		G (G)
Dibutyl phthalate, n-		X (X)
Dibutyl sebacate		X (X)
Dichlorobenzene		X (X)
Dichloroethylene		X (X)
Diesel oil		G (G)
Diethyl ethyl		G (G)
Diethylamine		X (M)
Diethylbenzene		X (X)
Diethylene glycol		M (M)
Diglycolic acid		X (X)
Dimethyl ether		G (G)
Dimethyl formamide (DMF)		X (M)
Dimethyl phthalate (DMP)		M (M)
Diethyl phthalate (DOP)		G (G)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Dioxane		X (X)
Ethyl acetate		X (X)
Ethyl acrylate		X (X)
Ethyl alcohol		X(X)
Ethyl benzene		X (X)
Ethyl ether		G (M)
Ethyl chloride		X (X)
Ethylene dichloride		X (X)
Ethylene glycol		M (M)
Ethylene glycol monoethyl ether (Carbitol)		X (X)
Ethylene oxide		X (X)
Ethylene trichloride		X (X)
Fatty acids, C>7		G (G)
Fatty Acids, C<7		X (X)
Ferric chloride		G (G)
Ferric nitrate		G (G)
Ferric nitrate		G (G)
Ferric sulfate		G (G)
Fluorine		X (X)
Fluorosilic acid		X (X)
Formaldehyde solution		X (X)
Formamide		X (X)
Formic acid	3%	G (G)
Formic acid	10%	M (G)
Formic acid	100%	X (X)
Freon F-11		X (X)
Freon F-12		G (G)
Freon F-22		X (X)
Freon F-113		G (G)
Fruit pulp		M (G)
Furfural		X (X)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Furfuryl alcohol		X (X)
Gallic acid		M (M)
Gasoline		G (G)
Gelatin		M (G)
Glucose		G (G)
Glue (bone glue)		G (G)
Glycerol		G (G)
Glycine		X (X)
Glycolic acid	30%	X (X)
Heptane		G (G)
Hexane		G (G)
Hexaldehyde		G (M)
Hexyl alcohol		M (X)
Hydrazine		X (X)
Hydrazine hydrate		X (X)
Hydrofluosililic acid		X (X)
Hydrobromic acid		X (X)
Hydrogen bromide		X (M)
Hydrogen chloride	15%	X (X)
Hydrogen chloride (Conc.)	38%	X (X)
Hydrogen chloride (gas)		X (X)
Hydrogen fluoride	10%	X (G)
Hydrogen fluoride	30%	X (G)
Hydrogen fluoride	73%	X (M)
Hydrogen peroxide	3%	G (G)
Hydrogen peroxide	10%	X (X)
Hydrogen peroxide	30%	X (X)
Hydrogen sulfide (wet and dry)		X (X)
Hydroquinone		X (X)
Hydroxylamine disulfate		X (X)
Iodine, tincture of		X (X)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Isobutanol		M (X)
Isobutyl acetate		X (X)
Isopropyl acetate		M (M)
Isopropyl alcohol		G (M)
Isopropyl ether		G (G)
Jet A		G (G)
JP-8, JP-5		G (G)
Kerosene		G (G)
Ketones		X (X)
Lactic acid		X (G)
Lanolin		G (G)
Lard		G (G)
Lauryl alcohol		X (X)
Lead acetate		M (M)
Lead nitrate		G (G)
Lead sulfate		G (G)
Linseed oil		G (G)
Lubricating oils		G (G)
Magnesium chloride		M (G)
Magnesium hydroxide		M (M)
Magnesium sulfate		G (G)
Magnesium sulfite		M (G)
Maleic acid		X (X)
Mercuric chloride		G (G)
Mercury		G (G)
Methane, gas		G (M)
Methyl acetate		X (X)
Methyl alcohol		X(X)
Methyl amine		X (X)
Methyl bromide		X (X)
Methyl chloride		X (X)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Methyl ethyl ketone		X (X)
Methyle isobutyl ketone		X (X)
Milk		G/(G)
Mineral oil		G (G)
Molasses		G (G)
Monochloroethane		X (X)
Morpholine		X (X)
Mustard		G (G)
Naphtha		G (G)
Naphthalene		G (G)
Nickel acetate		M (G)
Nickel dichloride		M (G)
Nickel sulfate		G (G)
Nitric acid	10%	X (X)
Nitric acid	25%	X (X)
Nitric acid	50%	X (X)
Nitric acid	60%	X (X)
Nitrobenzene		X (X)
Octane		G (G)
Oils and fats, vegetable		G (G)
Oleic acid		G (G)
Oleum		X (X)
Oleum steams		X (X)
Olive oil		G (G)
Ozone		G (G)
Palm oil		G (G)
Palmitic acid		G (G)
Paraffins		G (G)
Pectin		G (G)
Pentachlorophenol		X (X)
Pentanol		M (M)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Perchloric acid		X (X)
Phenol		X (X)
Phenyl ether		X (X)
Phenylbenzene		X (X)
Phosphoric acid	3%	G (G)
Phosphoric acid	50%	M (G)
Phosphoric acid	85%	X (X)
Phosphorus oxychloride		X (X)
Phthalic acid ester		X (M)
Picric acid		G (G)
Polychlorinated biphenyls (PCB)		G (G)
Potassium acetate		X (X)
Potassium borate		M (G)
Potassium bromate	10%	X (X)
Potassium bromide		M (M)
Potassium carbonate (Potash)		M (G)
Potassium chlorate		M (G)
Potassium chloride		G (G)
Potassium chromate	40%	X (X)
Potassium cyanide		M (G)
Potassium dichromate		M (G)
Potassium hydroxide	10%	G (G)
Potassium hydroxide	50%	X (M)
Potassium hydroxide	100%	X (X)
Potassium hypochlorite		M (G)
Potassium iodide		M (M)
Potassium nitrate		G (G)
Potassium perchlorate		X (X)
Potassium permanganate	10%	M (G)
Potassium persulfate		X (X)
Potassium sulfate		G (G)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X [Fuel] Ether = (X) [Water]
Propane, gas		G (M)
Propane, liquid		G (M)
Propargyl alcohol	7%	X (X)
Propionic acid		X (X)
Propyl alcohol		M (X)
Propyl amine		X (X)
Propylene glycol		X (X)
Propylene oxide		X (X)
Pyridine		X (X)
Salicylic acid		G (G)
Sea water		X (G)
Silicic acid		G (G)
Silicone oil		G (G)
Silver nitrate		G (G)
Soapy solution		M (M)
Sodium acetate		X (M)
Sodium bicarbonate		X (G)
Sodium bisulfate		X (X)
Sodium bisulfite		X (X)
Sodium borate		G (G)
Sodium chlorate		M (G)
Sodium chloride		M (G)
Sodium cyanide		M (M)
Sodium dichromate		M (M)
Sodium fluoride		M (G)
Sodium hydroxide	25%	X (M)
Sodium hydroxide	100%	X (X)
Sodium hypochlorite	10%	M (G)
Sodium hypochlorite	30%	X (M)
Sodium hypochlorite	100%	X (X)
Sodium nitrate		G (G)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING
		All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Sodium oxalate		X (X)
Sodium silicate		X (M)
Sodium sulfate		M (G)
Sodium sulfide		G (G)
Sodium thiosulfate		M (M)
Spruce oil		G (G)
Starch solution		G (G)
Starch syrup		G (G)
Stearic acid		M (G)
Styrene		X (M)
Sulfur trioxide		M (G)
Sulfonic acid		X (X)
Sulfuric acid	10%	M (M)
Sulfuric acid	50%	X (M)
Sulfuric acid	75%	X (X)
Sulfuric acid	90%	X (X)
Sulfurous acid	10%	M (M)
Sulfurous acid	75%	X (X)
Tallow		G (G)
Tannic acid		M (M)
Tartaric acid		M (M)
Tetrachloroethane		X (X)
Tetrachloroethylene		M (M)
Tetrahydrofuran (THF)		M (M)
Toluene		X (X)
Transformer oil		G (G)
Tributyl phosphate (TBP)		X (X)
Trichloroacetic acid (TCA)		X (X)
Trichloroethane		X (X)
Trichloroethylene (TRI)		X (X)
Tricresyl phosphate (TCF)		X (X)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

CHEMICALS	CONC.	RATING All values are @ 20°C. Values are given for both Ester and Ether based TPU: Ester = X Ether = (X)
Triethylene glycol		G (G)
Trioctyl phosphate		G (G)
Trisodium phosphate		M (M)
Urea		M (G)
Vegetable oils		G (G)
Vinegar		X (M)
Vinyl acetate		X (M)
Vinyl chloride		X (M)
Water		M (G)
Water, distilled		M (G)
Whiskey		G (G)
White Spirit		G (G)
Wines		M (G)
Xylene		X (X)
Zinc acetate		X (X)
Zinc chloride		M (M)
Zinc sulfate		M (M)

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.